

BLAST MEDIA DATA SHEET



GUYSON NAME	TURBOBEAD
COMPOSITION / DESCRIPTION	Carbon steel shot
SHAPE	Spherical
COLOUR	Silver / black metal
BLAST SYSTEMS	Turbine wheel and dry compressed air systems
HARDNESS	45 – 51 Rockwell C
TYPICAL APPLICATIONS	Cleaning, deburring and preparing ferrous surfaces. Shot peening.
SPECIAL NOTES	Low wear on blast machine and long media life. Most effective in turbine or pressure fed systems. Hard and resilient, this shot multiplies its effectiveness by the ricochet effect.
H & S DATA SHEET	24
SIZES AVAILABLE	Nominal Size Range (microns)
S070	180 – 350
S110	300 – 500
S170	420 – 710
S230	600 – 850
S280	710 - 1000
S330	850 - 1200
PACK SIZE	25 kg bag

Guyson International Limited ■ Snaygill Industrial Estate ■ Keighley Road ■
SKIPTON ■ North Yorkshire ■ BD23 2QR

Tel: 01756 799911 ■ Fax: 01756 790213 ■ E-Mail: info@guyson.co.uk